

Summary

		Nitrile.....			Silicone			Polyacrylate.....			FKM.....		
	OIL	Average Change	Standard Deviation	Original Change	Average Change	Standard Deviation	Original Change	Average Change	Standard Deviation	Original Change	Average Change	Standard Deviation	Original Change
Volume Change %	9G	0.2	0.1	-1.4			16.7	-2.0	0.2	-2.2			0.6
	J	-1.0	0.1	-0.7	26.3	0.1	8.3			-0.4	0.2	0.1	0.2
	P			0.8			18.8	-0.3	0.8	-1.0			0.0
	1006	-1.1	0.7	2.5	27.4	0.9	25.7	0.6	0.0	3.7	0.3	0.1	0.6
Points Hardness Change	9G	3.2	2.6	5.0			-13.0	2.9	1.3	4.0			2.0
	J	3.7	3.0	10.0	-19.1	0.7	-9.0			4.0	4.9	2.0	8.0
	P			0.0			-14.0	2.9	0.7	7.0			4.0
	1006	7.2	0.0	3.0	-18.1	2.3	-22.0	-1.7	1.4	-1.0	7.2	0.0	6.0
Tensile Strength % Change	9G	-0.9	3.4	-22.2			-15.9	4.5	4.5	3.4			-41.4
	J	-50.4	5.7	-61.1	4.5	3.8	-59.3			2.3	-55.1	18.6	-67.6
	P			-1.7			-11.1	-9.8	5.3	-13.4			-31.8
	1006	-33.8	2.3	-37.4	-2.2	2.9	-24.0	0.3	5.9	-2.5	-65.3	0.2	-68.8
Elongation Change %	9G	-28.9	6.5	-42.1			-14.4	-15.2	11.3	-15.6			-40.0
	J	-59.7	1.7	-63.6	-5.0	11.6	-22.7			-15.3	-53.7	16.5	-57.6
	P			-13.7			-11.1	-31.0	10.3	-42.7			-42.3
	1006	-56.9	2.3	-49.7	-14.0	9.9	-24.0	-10.5	4.3	-15.2	-54.2	1.1	-62.0